

# EUROPEAN PATENT OFFICE

## Patent Abstracts of Japan

#5

PUBLICATION NUMBER : 02104755  
PUBLICATION DATE : 17-04-90


APPLICATION DATE : 27-07-89  
APPLICATION NUMBER : 01192716

APPLICANT : ASAHI CHEM IND CO LTD;

INVENTOR : SHIMA TSUKASA;

INT.CL. : D04H 1/72 D04H 1/42

TITLE : ULTRAFINE FIBER WEB OF  
POLYESTER



ABSTRACT : PURPOSE: To obtain the title web suitable as ground fabric napped artificial leather having specific average fiber diameter and specific intrinsic viscosity, tenacity, excellent dyeability, flexibility and a little occurrence of polymer pilling, comprising a polyester polymer by melt blowing method.

CONSTITUTION: A polyester polymer (preferably polyethylene terephthalate) is melted by an extruder 1, extruded from a spinning orifice of a die 2 while blowing a high-temperature air flow upon the as-spun fibers to give the aimed web 5 having 0.8-5.0 $\mu$ m average fiber diameter, 0.45-0.80, preferably 0.50-0.70 intrinsic viscosity and preferably 3.0-6.0Y value. When intrinsic viscosity of ultrafine fiber  $\geq$  intrinsic viscosity of polyester-0.2 is satisfied, web having excellent weight distribution in the width direction is obtained.

COPYRIGHT: (C)1990,JPO&Japio